

USP 797 & 800 Compliance Specialists Everything you need to achieve and

maintain a compliant cleanroom environment

BioClean-C Non-Sterile Chemotherapy Protective Apron w/Sleeves

About

The BioClean-C[™] Chemotherapy Protective Apron with Sleeves provides maximum protection against a range of cytotoxic drugs. Manufactured from lightweight, low-linting and hard wearing CleanTough[™] material, the apron features an adjustable neck fastening, tie tapes at the rear, ultrasonically bonded sleeve seams with protective tape and 100% polyester elasticated cuffs.

Specifications

MATERIAL: CleanTough™ material

COLOUR: Blue

CONSTRUCTION: 100% polyester elasticated cuffs, ultrasonically bonded sleeve seams with protective tape

CLASSIFICATION: PPE Cat 3 Type PB [6]

CHARACTERISTICS: Low particulating

COMPATIBILITY: ISO Class 4

Features

- Tested against ASTM D6978-05 using a minimum of nine cytotoxic drugs
- Ultrasonically bonded seams with protective tape
- Tie tapes at rear
- · Adjustable neck fastening
- Processed to ensure ISO Class 4
 compatibility
- 100% polyester elasticated cuffs
- Lightweight, low-linting & hard wearing CleanTough™ material



www.carter-health.com 407.296.6689 info@Carter-Health.com

CHEMOTHERAPY





LIGHTWEIGHT & LOW-LINTING

TESTED AGAINST ASTM D6978-05

100% POLYESTER ELASTICATED CUFFS

ADJUSTABLE NECK FASTENING

ULTRASONICALLY BONDED SEAMS



Dr Isolator™ represents BioClean's™ GMP compatible Chemo Safety Wear





Carter-Health Disposables, LLC Phone: (407) 296.6689 Web: www.Carter-Health.com

Quality Standards

- Manufactured in a facility holding ISO 9001:2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 Complex Design Personal Protective Equipment
 PPE Directive 89/686/EEC
- Tested against standard EN ISO13034 protective clothing against liquid chemicals (Type PB[6])
- Tested against standard EN 14325 protective clothing against chemicals
- Tested against permeation standard ASTM D6978-05 for cytotoxic drugs
- Processed in an NEBB certified ISO Class 4 environment

Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

Performance Test Results

TEST	RESULT		PERFORMANCE CLASS (EN 14325)
Abrasion Resistance	10 to 100 cycles		1
Flex Cracking Resistance	5,000 to 15,000 cycles		3
Trapezoidal Tear Resistance	CD 42.5 N		3
Trapezoidal Tear Resistance	MD 58.4 N		3
Tensile Strength	CD 43 N		1
Tensile Strength	MD 68 N		2
Puncture Resistance	9 N		1
Repellence to Liquids	30% H ₂ SO ₄	99.0%	3
	10% NaOH	98.4%	3
	O-Xylene	91.4%	2
	Butan-1-ol	93.9%	2
Penetration by Liquids	30% H ₂ SO ₄	0%	3
	10% NaOH	0%	3
	O-Xylene	0%	3
	Butan-1-ol	0%	3
Seam Strength ¹	90 N		3

¹Seam not destroyed

Particle Shedding Test Results

TEST	RESULT	CATEGORY (IEST-RP-CC003.3)
Particle Shedding (Helmke Drum Test)	<1700	Category I







CleanTough™ Material - ASTM D6978-05 Test Results

Breakthrough detection time (minutes)

Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.01 µg/cm²/min

CISPLATIN	CARMUSTINE	CYCLO- PHOSPHA- MIDE	DOXO-RUBICIN HYDRO- CHLORIDE	5- FLUORO- URACIL	METHO- TREXATE	ETOPOSIDE	PACLITAXEL	THIOTEPA
>480	>480	>480	>480	>480	>480	>480	>480	>480

BCAS-S	Small	40 pc/cs
BCAS-M	Medium	40 pc/cs
BCAS-L	Large	40 pc/cs
BCAS-XL	X-Large	40 pc/cs

Product Numbers



